

ESLON®-DC ESD

POLYCARBONATE PC407AS

Static dissipative (antistatic) plastic sheets

PC407AS |  clear

ELECTRICAL

		Method		Unit	ESD-Standard
Surface resistivity	ASTM D-257	DIN 53482	IEC 60093	Ω/\square	$10^6 \sim 10^7$
Electrostatic discharge	MIL B-81705B			s	< 0.1
Dielectric constant	ASTM D-150	DIN 53483	IEC 60250		3

PHYSICAL

Density	ASTM D-792	DIN 53479	ISO 1183	g/cm ³	1.20
Water absorption	ASTM D-270	DIN 53495	ISO 62A	%	0.3
Pencil hardness	JIS K5400				HB
Grid adhesiveness	JIS D0202				100/100

OPTICAL

Light transmittance	ASTM D-1003		ISO 13468	%	83
Haze	ASTM D-1003		ISO 14782	%	2
Refractive index	ASTM D-542		ISO 489		1.59
Distinctness of image (DOI)	JIS K7105			%	90

MECHANICAL

Tensile strength	ASTM D-638	DIN 53455	ISO 527	MPa	67
Tensile elongation at break	ASTM D-638	DIN 53455	ISO 527	%	100
Flexural strength	ASTM D-790	DIN 53452	ISO 178	MPa	90
Flexural modulus	ASTM D-790		ISO 178	MPa	2300
Compressive strength	ASTM D-695		ISO 604	MPa	85.3
Charpy impact strength (23°C)			ISO 179-1	kJ/m ²	80
Notched impact strength (23°C)	ASTM D-256		ISO 180	J/m	847

THERMAL

Heat deflection temperature	ASTM D-648	DIN 53461	ISO 75	°C	135
Coefficient of linear thermal expansion	ASTM D-696		ISO 11359	mm/mm°C	7×10^{-5}
Thermal conductivity	ASTM C-177			W/mK	0.20
Specific heat	ASTM C-177			KJ/kgK	1.26
Heat shrinkage	JIS K6745			%	0
Flammability	UL 94				